



Trading International Industrial Pooya .co
Oil & Gas & Petrochemical

We are major supplier in kinds of grade bitumen 60/70 and other grade this products in Iranian FOB and other place CIF in world wide.



Bitumen 60/70

	Specification	Test method
Specific gravity @25/25 C	1.01-1.06	D-70
Penetration @25 C	60/70	D-5
Softening point C	49/56	D-36
Ductility @25 C	100 min	D-113
Loss on heating (wt)%	0.2 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point C	250min	D-92
Solubility in CS2 (wt)%	99.5 min	D-4
Spot test	negative	*A.A.S.H.O.T. 102



. We are only interested in serious, valid, financially capable buyers that can provide an LOI or ICPO,so we seek inquiries from end buyers, mandates or agents for any quantity, please contact us directly



+98-2188289093 and +98-9333105101

e-mail : info@gbf-pooya.com

site:www.gbf-pooya.com

tiipco